



# TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224

## DAP® HVAC Professional 100% RTV Silicone Sealant

### PRODUCT DESCRIPTION

**DAP® HVAC SILICONE** is a high-performance sealant designed especially for HVAC applications. It provides a long-lasting weather resistant seal with supreme adhesion, flexibility, and durability. It adheres to most common building materials and remains flexible from -40°F to 475°F. Meets Fed. Spec. TT-S001543A, ASTM C920, FDA Reg. No. 21 CFR 177.2600, and NSF/ANSI Standard 51. Safe for incidental food contact. Interior/exterior use.



PACKAGING	COLOR	UPC
10.3 fl oz (305 mL)	White	7079808010
10.3 fl oz (305 mL)	Clear	7079808011
10.3 fl oz (305 mL)	Aluminum	7079808012

### KEY FEATURES & BENEFITS

- 100% RTV silicone
- Remains flexible up to 475°F
- Will not crack or shrink
- 100% waterproof/weather resistant seal
- Meets Fed. Spec. TT-S001543A and ASTM C920
- Certified by NSF to NSF/ANSI Standard #51
- It is safe for incidental food contact. When cured and washed, the product meets FDA Reg 21, CFR 177.2600
- Interior/exterior use

### SUGGESTED USES

#### USE FOR:

- Air conditioners
- Ducts
- Furnaces
- Access doors
- Refrigerators
- Aluminum siding
- Flanged pipe joints
- Window & door frames
- Vents
- Pipes
- Flues



# TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224

## ADHERES TO:

- Most metals\*
- Ceramic
- Porcelain
- Marble
- Non-oily surfaces
- Glass
- Fiberglass
- Most plastics
- Painted surfaces
- Most common building materials

## FOR BEST RESULTS

- Application temperature range is between 0°F to 100°F.
- Not recommended for continuous underwater use, filling butt joints, surface defects, tuck-pointing, chimneys, stovepipes or fireplace applications. Not recommended for structural glazing.
- Not for oily woods or cementitious surfaces. Substrates made of methylmethacrylate, polycarbonate, polypropylene, polyethylene and polytetrafluoroethylene do not allow for best adhesion and compatibility with sealant. Try test area before using.
- Corrodes some metals. \*Not recommended for use on or near brass, copper or copper alloys, zinc, iron, galvanized metals or other surfaces prone to attack by weak acids.
- **Not paintable.** Paint surface substrate before applying sealant.
- Store below 80°F in dry place for optimal shelf life.

## APPLICATION

### Surface Preparation

Surface must be clean, dry, structurally sound and free of all old caulk, dirt, dust, & foreign material.

### Product Application

1. Cut nozzle at a 45° angle to desired bead size.
2. Puncture inner foil seal.
3. Load into caulk gun.
4. Fill gap or crack with sealant.
5. If necessary, tool or smooth the bead of sealant with a finishing tool before the sealant skins over.
6. Clean up excess wet sealant from surface and tools with mineral spirits. Scrape or cut away excess dried sealant. Do not use mineral spirits to clean hands or skin. Wash hands or skin with soap and water.
7. Reseal cartridge for storage and reuse.



# TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224

## TYPICAL PHYSICAL & CHEMICAL PROPERTIES

<b>Typical Uncured Physical Properties</b>	
Appearance/Consistency	Gunnable, non-sag paste
Base Polymer	Silicone rubber
Filler	Not applicable
Volatile	Not applicable
Weight % Solids	>97.0%
Density (lbs per gallon)	8.5
Odor	Vinegar-like
Flash Point	>212°F
Freeze Thaw Stability (ASTM C1183)	Will not freeze
Shelf Life	24 months
Coverage	56 linear feet at 3/16" bead size
<b>Typical Application Properties</b>	
Application Temperature Range	0°F to 100°F
Tooling Time (Working Time)	10 minutes
Tack Free Time	15 minutes
Full Cure	24 hours
Return to Service Time	12 hours
Vertical Sag (ASTM D2202)	0.05"
<b>Typical Cured Performance Properties</b>	
Service Temperature Range	-40°F to 475°F
Water Ready Time	12 hours
Paint Ready Time	Not paintable
Mildew Resistance	Cured sealant is mold & mildew resistant
Dynamic Joint Movement (ASTM C719)	+/- 25%



# TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224

## CLEAN UP & STORAGE

Remove excess uncured sealant from surfaces and tools with mineral spirits. Excess cured sealant must be cut or scraped away. Do not use mineral spirits to clean hands or skin. Wash hands or skin with soap and water. Store container in temperatures below 80°F and in a dry place.

## SAFETY

See product label or Safety Data Sheet (SDS) for health and safety information. You can request a SDS by visiting our website at [dap.com](http://dap.com) or calling **888-DAP-TIPS**.

## WARRANTY

**LIMITED WARRANTY:** If product fails to perform when used as directed within one year of purchase, call 888-DAP-TIPS, with your sales receipt and product container available, for replacement product or sales price refund. DAP Products Inc. is not liable for incidental or consequential damages.

## COMPANY IDENTIFICATION

**Manufactured for:** DAP Products Inc., 2400 Boston Street, Baltimore, Maryland 21224

**Usage Information:** Call 888-DAP-TIPS or visit [dap.com](http://dap.com) & click on “Ask the Expert”

**Order Information:** 800-327-3339 or [orders@dap.com](mailto:orders@dap.com)

**Fax Number:** 410-558-1068

**Also, visit the DAP website at [dap.com](http://dap.com)**